

OK Serralheiro



Rutile coated electrode designed for special work in locksmith shop. It is dedicated for all types of joints, even without preparation, in all positions. Applicable to steel structures, galvanized sheets and buildings in general, with stable arc, low spatter and easy slag removal, making the work more productive. It produces coils with excellent finish. Because the facility of opening and reignition of arc, this electrode excellent for kickings. It also provides low smoke and great performance.

Classificações	AWS/ASME SFA 5.1: E6013
Aprovações	AWS/ASMESFA 5.1 E 6013

As aprovações são baseadas em cada unidade de produção. Para mais informações, contate a ESAB.

Corrente de Soldagem	DC+-, AC
Tipo da Liga	CMn
Tipo de Revestimento	Rutile

Deposição

Diâmetro	Corrente	Tensão
2.5 mm	75-110 A	20-30 V
3.25 mm	85-160 A	20-30 V
4 mm	110-200 A	20-30 V